

## Performance Summary

- Enhanced soil + stain resistance
- Enhanced abrasion resistance
- Fluid barrier
- Bleach-solution cleanable
- Enhanced fade resistance
- No antimicrobial additives
- No flame retardant additives

## Cleaning and Maintenance

Cleaning Code: **(W-S)** For water-based stains use water-based cleaners. For oil-based stains use solvent-based cleaners. We recommend using a professional cleaning service.

Bleach solutions of up to 10% may be used for more difficult stains.

For additional cleaning information visit [cfstinson.com](http://cfstinson.com)

For complete specifications visit [cfstinson.com](http://cfstinson.com)

Dye lots may vary slightly.

\* This term and any corresponding data refer to the typical performance in the tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

\*\* Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

## Specifications



Content	Vinyl Surface with Polyester Backing
Finish	Advanced Soil and Stain Resistant Top Coat
Backing	Polyester
Weight	30.0 oz./lin. yd. ± 1.0 oz.
Width	54 inches
Roll Size	30 yards

## Performance Characteristics

Abrasion Resistance** ASTM D-4157	Exceeds 100,000 double rubs - heavy duty
Adhesion ASTM D-751	Warp: 3.3 lbs. min., Fill: 3.3 lbs. min.
Break Strength CFFA-17	Warp: 121 lbs. min., Fill: 72 lbs. min.
Tear Strength CFFA-16	Warp: 5.6 lbs. min., Fill: 5.9 lbs. min.
Seam Slippage CFFA-14	Warp: 46 lbs. min., Fill: 35 lbs. min.
Colorfastness to Light CFFA-2	1000 Hours, Class 4.5
Fluid Barrier	Inherent Fluid Barrier

## Flammability\*

California Technical Bulletin 117-2013 Section 1	Passed
UFAC	Class 1
NFPA 260	Class 1

This product is formulated without phthalates.



# Stinson®

C.F. Stinson, LLC  
2849 Product Drive  
Rochester Hills, MI 48309

P 800 841 6279  
F 248 299 3884

[cfstinson.com](http://cfstinson.com)